



# TK-TRI-KOTE 26 UV

## Chlorinated Rubber Epoxy Concrete Treatment

Item No. TK-26 UV

### PRODUCT DESCRIPTION

TK-TRI-KOTE 26 UV is a special formula of chlorinated rubber and epoxy that cures, seals and hardens new or existing concrete in one easy application. TK-TRI-KOTE 26 UV eliminates the need for further curing processes by retaining 95-98% of the moisture content of concrete over its critical 7-day curing period - ensuring stronger, fully cured surfaces. TK-TRI-KOTE 26 UV contains UV (ultra violet) inhibitors which resist yellowing or discoloration due to sunlight exposure.

#### Features:

- Adverse weather conditions such as low humidity and high temperatures will not affect its performance (when applied at the proper time).
- Penetrates as deep as 3/16" below the surface on existing concrete.
- Provides complete protection from sudden rainfall within one hour of application, as well as continuous protection from damage caused by freeze/thaw cycles, deicing chemicals, mild acids and alkali, salt, grease and oil.
- Arrests popping and retards spalling, flaking and other serious surface disintegration.
- Eliminates dusting in new concrete and stops dusting, flaking and leaching of free alkali in existing concrete.
- Provides a semi-gloss, easy to maintain finish.

### USES:

Suitable for interior or exterior use on new or existing concrete in industrial, commercial, farm and residential environments. TK-TRI-KOTE 26 UV has been tested and performance proven throughout the United States and Canada by multiple state highway departments, federal construction projects, and county and municipal projects.

### APPLICATION PROCEDURES:

#### PREPARATION:

Surfaces must be clean, dry and free of oils, grease and dust. Large areas may be blown dust free by compressed air, washed and let dry. Surface water must be allowed to completely dissipate before applying.

At this point a small mock-up area should be applied in an inconspicuous location to test the compatibility of the coating with the prepared substrate. Allow the coating to dry and cure fully, then inspect for proper film formation, gloss, adhesion and confirm that the film is free from whitening or any other defects.

#### MIXING:

The material is ready for use and requires no mixing or dilution. It is unlawful to further dilute with non-exempt solvents.

#### APPLICATION:

TK-TRI-KOTE 26 UV WILL DARKEN CONCRETE.

*New Concrete Application* - Finish trowel and allow surface water to completely dissipate. Use a low pressure (20-30 lbs.) sprayer or power sprayer and apply uniformly at the specified rate of coverage. Avoid heavy accumulations. **DO NOT OVER APPLY.**

*Existing Concrete Application* - Use a long nap applicator or paint roller to distribute the compound more evenly. An airless sprayer or low pressure spray equipment may be used for larger areas but avoid heavy accumulations. **DO NOT OVER APPLY.** On very porous surfaces where absorption is rapid, a second coat should be applied. Allow the coating to become tack free between coats.

#### CLEAN UP:

Use TK-00 XYLENE\* to clean tools and equipment. Pump solvent through the sprayer to remove residue of materials which can clog the hose and wand assembly.

### TECHNICAL DATA

*Composition and Materials: A special formula of chlorinated rubber and epoxy. No fillers are used and there are no oils, waxes or saponifiable resins. TK Products are manufactured with only the finest quality raw materials available and close quality-control is practiced.*

Solids Content:	29%
Flash Point:	76°F
Moisture Efficiency:	.10 kg/m <sup>2</sup> at 300 ft <sup>2</sup> /gallon
Drying Time* (70°F & 50% RH):	1 hour
VOC Content:	< 700 g/l
A.I.M. Category:	Concrete Curing and Sealing Compounds Maximum VOC 700 g/l
Applicable Standards:	- ASTM C-1315, Type I, Class A, B & C - ASTM C-309, Type I, Class A & B and Type ID with a red dye added. - Fed. TTC-C-800A, Type II, Class I - AASHTO Des. M-148, Type I, Clear - CE CRD-C-300, Type I - State Highway Departments (check local district offices) - USDA Authorization for use in meat, poultry and food processing plants. - Resilient Tile Institute approval for compatibility with most resilient tile, carpet adhesives and paints.

\*Cooler temperatures and high humidity rates will extend dry times.

## COVERAGE:

Surface	Coverage	
Curing	Troweled	450-550 sq.ft./gal
	Broomed	350-450 sq.ft./gal
Dustproof/Seal:	250-650 sq.ft./gal	
Second Coat (if necessary):	250-650 sq.ft./gal	

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

## MAINTENANCE:

Minimal maintenance is required other than occasional sweeping, dusting or mopping. If wear patterns do occur or if spillage removes the coating, TK-TRI-KOTE 26 UV may be reapplied to the affected area(s).

## LIMITATIONS:

- Apply in temperatures above 40°F. Colder weather applications may be made under prescribed conditions and procedures specified by TK Products.
- Not recommended for use on asphalt or colored concrete.
- Not recommended for use on concrete overlays or thin set mortar.
- Sprayers must be equipped with neoprene hose, washers and gaskets as rubber or other materials will disintegrate from the solvent.
- Material will not freeze and may be stored outdoors in cold weather, however it must be allowed to warm to approximately 50°F before use.
- This product is to be applied according to recommended coverage rates as over-application may cause discoloration.

*Note 1. Concrete containing calcium chloride will remain dark longer when sealed. Extenders and additives (concrete admixes, fly ash) are now being added to some ready mixed concrete which can cause inconsistency in the porosity of the concrete. Some areas of the finished concrete may then appear darker than others. To compensate for these variations, coverage ratios should be adjusted.*

*Note 2. Popout problems can occur anytime, however, concrete in certain regional areas, concrete applied in extremely hot conditions (90°F+), and heavily steel troweled concrete can aggravate popout problems. These deficiencies are the result of a heat caused reaction, called alkaline silica reactivity (ASR), between the silica in the shale particles of the fine aggregate with the sodium and potassium alkali in the portland cement. For more information on this problem, refer to "POPOUTS" by Norman E. Henning, P.E. and Kenneth L. Johnson, P.E. of Twin City Testing and Engineering Laboratory and Lowery J. Smith of the J.L. Shiely Company. Where this type of shale is present, and extremely hot weather conditions prevail, it is recommended that liquid membrane curing compounds should not be used until the concrete has been completely cured by water ponding, continuous water spray mist, or wet burlap covering for a period of three days. A seal coat can then be applied for dustproofing and protection (when concrete is completely dry).*

## FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

## AVAILABILITY:

TK-TRI-KOTE 26 UV is available through TK Distributors. Contact TK Products for the nearest distributor.  
Packaged in 55-gallon drums, 5-gallon pails and 1-gallon cans.

FOR PROFESSIONAL USE ONLY

## NOTES:

\*TK-00 XYLENE must be purchased separately

03/15 Last Rev. 09/14

## CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. **SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

## TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.