

# TK-EPO™ EXCEL PATCH

## Patching and Repair Epoxy/Urethane Hybrid

Item No. TK-EPO EXCEL

### PRODUCT DESCRIPTION

TK-EPO™ EXCEL PATCH is a rapid setting, 100% solids, high strength epoxy/urethane hybrid used to repair and patch concrete in a variety of applications.

#### Features:

- Complete patching and repair system (including aggregate) for spalled and deteriorating surfaces
- Working temperature of -20°F to 85°F
- Rapid setting - open to traffic in 12-15 minutes
- Convenient 1:1 mix ratio (by volume)
- Pre-measured kit for ease of use on the jobsite

### USES:

TK-EPO™ EXCEL PATCH is used for small patching and repairs on concrete bridge decks, parking ramps and decks, traffic areas, freezer floors, airport runways, taxiways and aprons.

### APPLICATION PROCEDURES

#### PREPARATION:

The surface must be clean, **dry** and in sound condition. Clean the area of all debris or contaminants including oils, grease, dust, dirt and unsound concrete. Vacuum or blow dust/debris off the surface using compressed air.

Expose clean, rough concrete for proper adhesion and best end results. Sandblasting may be necessary to expose clean concrete.

Cut or chip a vertical edge (minimum 1/2" deep) around the perimeter of the patching area.

#### MIXING:

Assemble all components and tools required for application, and ensure that the patching area is properly prepared before mixing. Mixing tools, containers and the patching area must be completely dry prior to use. Mix only the quantity of material which can be used within the pot life of the material.

Mixing Full Kits - Shake component "B" individually for 30 seconds, then combine components "A" and "B" and mix for 30 seconds at 200-300 rpm using a jiffy mixer with a 1/2" drill. Begin incorporating component "C" (aggregate) and mix for an additional 30 seconds or until aggregate is fully wetted out. Place product IMMEDIATELY.

Mixing Partial Kits - Shake component "B" individually for 30 seconds, then combine equal parts (1:1 ratio) of components "A" and "B" and mix vigorously for 30 seconds. Add 3-parts (by volume) of component "C" (aggregate) to 1-part of the mixed "A" and "B" component, and mix for an additional 30 seconds or until aggregate is fully wetted out. Place product IMMEDIATELY.

#### APPLICATION:

This is a rapid setting product, and as such the applicator

### TECHNICAL DATA

Pot life (100 grams at 73°F):	3 minutes
Viscosity (neat):	250 cps

### TESTING DATA

Applicable Standard	Product Performance
<b>ASTM D2240:</b> Shore Hardness	60-70
<b>ASTM D412:</b> Strength: Tensile Elongation:	1,500 psi 30%
<b>ASTM C579</b> (w/aggregate): Compressive Strength	3,500 psi
<b>ASTM C882:</b> Bond Strength	2,000 psi

should work quickly to complete application while the product is still pliant.

Finishing - TK-EPO™ EXCEL PATCH should be tamped into the entire patch area with the blunt end of 2"x4" or similar object to properly wet the substrate. The surface should then be troweled and finished immediately. A small amount of aggregate may be withheld from the mixture for sprinkling overtop the finished surface immediately upon troweling to achieve proper surface color and texture. The finished patch should be level and must not protrude above the surface of the surrounding area. TK-EPO™ EXCEL PATCH may be ground to achieve uniform grade.

Grinding to Finish Grade - IMPORTANT! Allow the patch to set for approximately 20 minutes or until hardened before grinding. For best results, use a flexible grinding wheel to grind smooth and level with the finished grade. Shaving, scraping or cutting may also be performed with a sharp razor blade. Cut as soon as the product is set but before it has fully cured.

#### CLEAN UP:

Empty containers must be drip-free. Cured material may be stripped and peeled from plastic tools and containers and may be disposed of without restriction. Excess liquid "A" and "B" materials should be mixed together and allowed to cure before being disposed of in the normal manner. It is recommended that metal tools be cleaned within one hour of use by cutting and peeling cured material from tools.

#### LIMITATIONS:

- TK-EPO™ EXCEL PATCH IS MOISTURE SENSITIVE AND SHOULD NOT BE APPLIED TO WET OR DAMP SUBSTRATES.

- Mix only quantities that can be used within the pot life of the material.
- Do not store in temperatures above 85°F (29°C) or in direct sunlight.

**PRECAUTIONS:**

**First Aid**

- EYE CONTACT: Flush immediately with water for at least 15 minutes and contact a physician immediately.
- RESPIRATORY CONTACT: Relocate person to fresh air.
- SKIN CONTACT; Remove any contaminated clothing. Remove epoxy immediately with a dry cloth or paper towel. Solvents should not be used as they carry irritant into the skin. Wash area of contact thoroughly with soap and water.
- Wash clothing before re-use
- CURED EPOXY RESINS ARE INNOCUOUS.

**FIRST AID:**

- Consult this product’s safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

**AVAILABILITY:**

TK-EPO™ EXCEL PATCH is available through TK Distributors. Contact TK Products for the nearest distributor.

Packaged in pre-measured 0.45 cubic foot (0.012m³) kits.

Storage Conditions: Shelf life is 12 months in original unopened containers. Store below 85°F (29°C).

Condition material to 65°F-85°F (18°C-29°C) before using.

FOR PROFESSIONAL USE ONLY

11/16 Last Rev.04/15

**CONDITIONS OF SALE/ LIMITED WARRANTY**

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products’ product by others and other factors affecting product performance are beyond TK Products’ control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS’ PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS’ PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

**TK DISCLAIMER:**

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.



**TK Products Construction Coatings**

11400 West 47th Street Minnetonka, MN 55343  
800-441-2129 toll free | 952-938-8084 fax | www.tkproducts.com