



TK-HI-TECH V

100% Epoxy for Vertical Applications

(to replace TK-Hi-Tech Plus)

PRODUCT DESCRIPTION

TK-HI-TECH V is a solvent-free, high-build, high solids, 100% epoxy/amine system designed specifically for vertical concrete applications where maximum durability and chemical resistance are needed. The high-gloss finish is available in both clear and ready-made standard colored formulations.

Features:

- Forms a tough, high strength coating that is resistant to abrasion.
- Resistant to damage caused by exposure to alkalis, solvents, acids, salt solutions and water, fats, oils and fuels.
- Formulated with resins which work as an adhesive within the substrate, strengthening it around minor cracks, crevices and weak spots.
- Virtually odor-free during installation and curing, making it ideal for interior applications.
- Low maintenance, high-gloss finish is smooth, durable and easy to clean.
- Easy, user-friendly roller application.

USES:

Suitable for interior use on properly prepared vertical concrete, drywall or steel surfaces subjected to abrasion, chemical/corrosive attack, or for areas in which a glossy, attractive and durable coating is desired.

APPLICATION PROCEDURES:

PREPARATION:

Surfaces should be clean, dry and properly prepared/primed. Glossy surfaces should be sand blasted or abraded.

MIXING:

- 1) Stir components "A" and "B" separately before combining together.
- 2) Using a 1:1 mix ratio, thoroughly combine components "A" and "B" in a clean container and mechanically mix for 2 minutes, scraping sides and bottom of the container (note that longer mixing times will reduce working time). Avoid whipping air into this mixture.
- 3) Mix only in quantities that can be used within the pot life time.
- 4) No induction time is required and this product is ready to use immediately. Do not thin.

APPLICATION:

Apply by airless or conventional spray, brush, high quality roller. Apply in a uniform manner and maintain a wet edge to prevent lap marks. To prevent outgassing, ensure that the concrete is completely dry and that the coating is being applied as the substrate is cooling. If a second coat is desired, recoat within 24 hours.

TECHNICAL DATA

Composition and Materials:	A solvent-free, high solids, 100% epoxy/amine system	
Viscosity:	2000-5500 cps	
Solids by Weight:	> 99%	
Gloss at 60° Angle:	80 minimum	
Pot Life:	40-75 minutes (at 75°F)	
Flash Point:	N/A	
Dry Time:	Tack Free	4-8 hours
	Recoat	24 hours
	Full Cure	48-72 hours
VOC Content:	< 20 g/l	
A.I.M. Category:	Nonflat Coatings, Interior Maximum VOC 380 g/l	

CLEAN UP:

Clean tools and equipment with TK-99 SUPER SOLVENT* OR TK-00 XYLENE* before the material dries.

COVERAGE:

Typical coverage rate is 350-450 square feet per gallon. Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

LIMITATIONS:

- Surface and ambient temperatures should be above 50°F for the epoxy to cure properly.
- Concrete must be completely cured and dry before application.
- Do not apply over surfaces that are frozen, structurally unsound or where water or water vapor is being transmitted through the concrete.
- Do not use on asphalt.
- Designed for indoor use as it may yellow slightly or chalk if used outdoors.
- Do not use once pot life has expired.
- Do not mix freshly catalyzed material with previously catalyzed material.
- Do not thin or reduce with solvents.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-HI-TECH V is available through TK Distributors. Contact TK Products for the nearest distributor.

Available in clear and ready-made standard color options. Contact your representative for color availability.

Packaged in 10-gallon kit and 2-gallon kit units.

Kit Contents:

10-gallon Kit: (2) 5-gallon pails

2-gallon Kit: (2) 1-gallon cans

FOR PROFESSIONAL USE ONLY

NOTES:

*TK-99 SUPER SOLVENT must be purchased separately

*TK-00 XYLENE must be purchased separately

02/17 Last Rev. N/A

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. **SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.