



TK-CONCRETE FORM SURFACE RETARDER

As Used to Create Vertical Aggregate Surfaces

Item No. TK-6100

PRODUCT DESCRIPTION

TK-CONCRETE FORM SURFACE RETARDER is a water based, in-form cement set concrete surface retarder for application to freshly placed vertical concrete surfaces. It chemically retards, or delays, the set of the concrete to allow the top layer (known as surface mortar) to be removed revealing an attractive exposed aggregate finish.

Features:

- Removal of the film leaves behind the natural aggregate, sands and stones in the concrete to reveal a decorative aggregate finish.
- Provides from 1/8" to 3/16" depth retardation.
- Safe for use and easy to apply.
- Does not reduce the life and reuse of the form like standard solvent-based in-form retarders.
- Reduces costs by eliminating surface preparation necessary for subsequent coatings or methods.
- Odor and VOC free.

USES:

Suitable for use on vertical, in-form concrete, patio block, steps and stoops. Due to its high concentration of complex inhibitors, it may also be safely used on steel, plastic, rubber, elastomeric and styrofoam form liners.

APPLICATION PROCEDURES:

MIXING:

Thoroughly and vigorously mix the contents of the container using a flat paddle or electric paint mixer.

APPLICATION:

Apply TK-CONCRETE FORM SURFACE RETARDER to the form by brush, roller or airless sprayer at 4-6 wet mils and in a uniform manner. When applying by brush or roller, two thin coats are recommended with the second coat being applied in the opposite direction of the first. Be sure to allow sufficient drying time between coats. When applying by sprayer, one full-bodied coat will be adequate.

Once applied, allow TK-CONCRETE FORM SURFACE RETARDER to dry thoroughly (15-45 minutes), then place concrete into the form and vibrate immediately. Do not use the vibrator as a means to move concrete inside the form as this will cause the retarder coating to break away from the form. Allow to cure.

NOTE: TK-CONCRETE FORM SURFACE RETARDER resists heat up to 140°F.

FINISHING:

Strip the concrete upon an adequate curing cycle. Removal of the surface matrix from the concrete can now be easily accomplished by pressure washing, dry brush or light sandblasting. For best results, remove surface matrix approximately one hour after stripping.

Clean forms by scraping off any residual retarder and/or surface matrix within one hour of stripping to avoid hardening on the form.

CLEAN UP:

Clean tools and equipment with water before the material dries.

COVERAGE:

Typical coverage rate is 150-200 square feet per gallon.

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

LIMITATIONS:

- When concrete is to be dropped into forms, or if a vibrator is to be used, TK-CONCRETE FORM SURFACE RETARDER should not be incorporated. The film and/or form will break and move with the concrete, causing an unevenly exposed surface.
- PROTECT FROM FREEZING.

TECHNICAL DATA

Appearance:	Viscous liquid
Odor:	Odor free
Specific Gravity:	1.03
Drying Time*:	15-45 minutes
V.O.C. Content:	0 g/L
A.I.M. Category:	Concrete Surface Retarders Maximum VOC 780 g/l

* Drying times are dependent on temperature and humidity rates.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-CONCRETE FORM SURFACE RETARDER is available through TK Distributors. Contact TK Products for the nearest distributor. Packaged in 55-gallon drums, 5-gallon pails and 1-gallon cans.

FOR PROFESSIONAL USE ONLY

07/17 Last Rev. 03/15

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. **SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

**TK Products**

11400 West 47th Street Minnetonka, MN 55343
800-441-2129 toll free | 952-938-8084 fax | www.tkproducts.com