

IAPMO UEL - 5006

VOC Regulatory Compliance:



TK-AIRMAX® 2102

Non-Permeable Air Barrier

Fluid Applied Air and Vapor Barrier | Division 7: Section 072726

Item No. TK-2102

ISO 9001 CERTIFIED

PRODUCT DESCRIPTION

TK-AIRMAX® 2102 NON-PERMEABLE is a high performance, solvent based, liquid applied air/vapor barrier for commercial cavity walls. It prohibits movement of air through the building envelope, resulting in energy savings, while also restricting moisture condensation which could lead to structural damage, mold or mildew.

Features:

- Coating dries quickly.
- Provides a continuous air/vapor and water barrier and a continuous water drainage plane flashed to discharge to the exterior of the structure.
- Elastomeric, long-lasting, and suitable for a wide variety of surfaces.
- Minimizes air movement through exterior walls resulting in energy savings.
- Chemically resistant to algae, bacteria, alkalis, acids and degradation from freeze/thaw cycles.
- Provides UV resistance for 12 months.

USES:

Suitable for use on commercial cavity walls. May be applied to any properly prepared exterior concrete, block, plywood, green treated wood, OSB board and exterior grade gypsum sheeting.

APPLICATION PROCEDURES: PREPARATION:

Material is ready for use and requires no mixing unless signs of separation are observed. It is unlawful to further reduce with non-exempt solvents. A clean, dry and frost free surface is required.

New Concrete preparation - New concrete should be allowed to cure until free moving or bleed water has completely dissipated. Concrete block and walls that have been laid or poured late in the year should be allowed to gain sufficient strength for proper adhesion with this product.

Existing Concrete preparation - Existing concrete surfaces must be thoroughly cleaned prior to application. All previous coatings and foreign materials must be removed.

EQUIPMENT:

A typical sprayer is a Graco 733/833, or a pneumatic airless sprayer with a working pressure of 3500 psi and a 45:1 lower unit capable of delivering 3 gallons per minute. Use a combination of a 1/2" and 3/8" pressure rated hose with a tip size of .035 to .039. Brush and/or roller application will work on smaller jobs or touch ups.

APPLICATION:

Masonry:

CMU mortar must be tooled at a minimum. Any voids, form tie holes and honeycombed areas should be filled and

Composition and Materials: % Solids by Weight: 44-45% Flash Point: Flammable, less than 100°F Drying Time:	-	TECHNICAL DATA
Flash Point: Flammable, less than 100°F		A rubberized polymer blend
	% Solids by Weight:	44-45%
Drying Time:	Flash Point:	Flammable, less than 100°F
Tack Free 1 hour Full Cure 24-48 hours		
VOC Content: < 600 g/l	VOC Content:	< 600 g/l
A.I.M. Category: Waterproofing Sealers and Treatments Maximum VOC 600 g/I	A.I.M. Category:	

TESTING DATA			
Applicable Standard	ASTM or ABAA requirements	Product Performance	
ASTM E2178: Air Performance of Building Materials	<0.004 CFM/ft ²	0.004 CFM/ft ²	
ASTM E2357: Air Leakage of Air Assemblies	<0.20 L/(s•m²) @ 75 Pa	0.004 L/(s•m²) @ 75 Pa 0.0008 CFM/ft²	
NFPA 285: Fire Propagation Characteristics	Pass/Fail	Pass	
ASTM E84: Surface Burning Characteristics	N/A	Class A, <25 flame spread Class A, <450 smoke spread	
ASTM E96-00: Water Vapor Transmission/ Vapor Permeability, Method B	(Declared Value)	Permeance 0.05 Perms V Permeability 0.0015 perm inch	
ASTM C1305: Crack Bridging Ability	Pass	Pass - no cracking/loss of adhesion after 10 cycles	
ASTM C1306: Hydrostatic Pressure Resistance	N/A	Passed long-term test	
ASTM C1522: Extensibility After Heat Aging	N/A	No cracks, tears or holes	
ASTM D412: Vulcanized Rubber/ Thermoplastic Elastomers	N/A	637%	
ASTM D2939: Resistance to Water	N/A	No blistering or soften- ing	
ASTM C836-03: Adhesion Strength	1.0 lbf/inch	11.9 lbf/inch	
AATCC Test Method 127: Water Resistance	Pass	Pass	
ASTM D 1970: Self Sealability	Pass	Pass	

repaired. Use a brush to remove loose mortar, smears and dirt that will affect proper adhesion. Remove mortar droppings from form ties and anchors. Apply TK-AIRMAX® 2102 NON-PERMEABLE by spray, brush or roller directly to the surface.

Exterior Gypsum Sheeting:

Apply by spray, brush or roller directly to exterior sheathing panels (i.e. exterior drywall, oriented strand board (OSB) plywood and glass faced board). Fasten corners and edges with appropriate screws. Fasteners should be driven flush with the panel surface rather than countersunk. It is recommended that all joints and seams be pre- or post-caulked with TK-SUPER SEAL PE $^{\text{TM}}$ or taped with TK-CLIMATE FLASH $^{\text{TM}}$ or TK-BUTYL BOND $^{\text{TM}}$. All gypsum corners need to be taped with TK-CLIMATE FLASH $^{\text{TM}}$.

Penetrations:

Transition and Control Joints - Joints between 1/32" and 3/8" should be pre- or post-caulked with TK-SUPER SEAL PE™. Allow caulking membrane to cure before applying TK-AIRMAX® 2102 NON-PERMEABLE by spray, brush or roller.

Larger Joints - Joints larger than 3/8" should be detailed with TK-CLIMATE FLASH $^{\mathbb{M}}$.

Flanges for Windows and Doors:

Flanges may be connected using one or a combination of the following: TK-SUPER SEAL $PE^{\mathbb{T}}$ or TK-CLIMATE FLASH.* *Details for proper application are available on the TK Products website.

Large Openings:

Openings greater than 3/8" should be covered with TK-CLIMATE FLASH™ after coating the substrate with TK-AIRMAX® 2102 NON-PERMEABLE and allowing the membrane to dry. On expansion joints, apply TK-AIRMAX® 2102 NON-PERMEABLE directly to the substrate, allow to cure, then apply TK-CLIMATE FLASH™ overtop the cured membrane.

COVERAGE:

Note that the coverage rate is inversely affected by the texture and porosity of the substrate, therefore substrates that are very porous will result in lower coverage rates (less square foot per gallon coverage). One coat of TK-AIRMAX® 2102 NON-PERMEALBE is sufficient when applied at 36-40 square feet per gallon, or 40-45 wet mil film. Any area that is thin may be recoated. Total cured coating will be 18-24 dry mils.

CLEAN UP:

Use TK-00 XYLENE to clean tools and equipment. Pump solvent through the spray equipment to remove material residue which can clog the hose and wand assembly.

LIMITATIONS:

- SAFETY PRECAUTIONS: A fitted organic/carbon filter respirator, and appropriate eye protection, must be worn at all times during application of this product.
- This product may be applied in temperatures ranging from 0°F to 100°F.
- Do not apply to rigid insulation or over silicone rubber sealants or caulks.
- This product should be fully cured before installation of rigid insulation overtop the membrane.
- This product is not resistant to aromatics, ketones or estertype solvents.
- If applying by brush or roller, multiple coats may be necessary to achieve proper coverage.

FIRST AID:

 Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available throughTK distributors, the TK office and the TK website.

AVAILABILITY:

TK-AIRMAX® 2102 NON-PERMEABLE is available through TK Distributors. Contact TK Products for the nearest distributor.

Available in Dark Gray color.

Packaged in 55-gallon drums and 5-gallon pails.

AIRMAX® SYSTEM DETAIL ACCESSORY PRODUCTS

The following tapes and caulks have been developed as accessory products for the AIRMAX® System

- CLIMATE FLASH™ Flashing Tape
- SUPER SEAL PE™ Polyether Joint Sealant
- SS Flashing™ Stainless Steel Flashing
- TWF-18™ Stainless Steel Thru Wall Flashing

Please visit the TK Products website for more information, or to access technical data sheets for these products.



11/17 Last Rev. 08/1

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express of implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

