



TK-EPOXY WATERPROOFING COATING

Waterproofing Sealer and Treatment

Item No. TK-2671 Low Solids/TK-2675 High Solids

PRODUCT DESCRIPTION

TK-EPOXY WATERPROOFING COATING is a two-component, penetrating, waterproofing, epoxy resin sealant for concrete. Formulated as a preventative treatment - although it may also be used for maintenance and repair work - TK-EPOXY WATERPROOFING COATING prevents corrosion and deterioration of concrete (and re-bar) due to moisture infiltration and chloride ion attack.

Features:

- Penetrates the surface to provide ultimate protection from within.
- Prevents costly corrosion and damage caused by moisture, chemicals, grease or oils.

USES:

Suitable for interior or exterior use on new or existing concrete highways, bridge decks, parking ramps, bus/truck terminals, median strips and barriers, industrial buildings and airport runways.

APPLICATION PROCEDURES:

PREPARATION:

Remove all foreign matter from the surface including grease, oil, curing compounds, weak sections and laitance. Oil and grease may be removed with a very hot solution of TK-CHEMICAL CLEANER 101*. Curing compounds may be removed with TK-00 SOLVENT* followed with a thorough hosing of clear water. Weak and deteriorating concrete can be scarified, grit blasted, bush hammered or removed by adequate mechanical means.

MIXING:

The mixing ratio for the two-components is 1:1 mixed by volume, not weight. TK-EPOXY WATERPROOFING COATING will blend better if both components are at or above 50°F. Do not mix more of the sealant than can be used during the pot life of the material.

Stir each component individually before blending the two together using a low powered mechanical mixer. If hand mixing with a stirrer, it must be done thoroughly to ensure uniform curing and best results. After blending, allow the material to set for 30 minutes. This induction period, along with thorough blending is necessary for maximum performance of the material.

APPLICATION:

Apply with a conventional sprayer, airless spray or roller. Additional coats may be applied after the previous coat has become tack free. Skid and wear resistance may be achieved by scattering silica sand over the final coat using a rate of 1 to 1-1/2 pound per square yard.

TECHNICAL DATA

TK-2671 Low Solids physical properties:

Solids by Weight:	37.2%
Color:	Clear amber
Pot Life:	2-4 hours (1-gallon mix)
Viscosity:	15-40 cps
Weight per Gallon:	Part A - 8.5 lbs. Part B - 7.25 lbs.
VOC Content:	< 600 g/l
A.I.M. Category:	Waterproofing Sealer and Treatment Maximum VOC 600 g/l

TK-2675 High Solids physical properties

Solids by Weight:	50.3%
Color:	Clear amber
Pot Life:	2-4 hours (1-gallon mix)
Viscosity:	< 30 cps
Weight per Gallon:	Part A - 8.74 lbs. Part B - 7.22 lbs.
VOC Content:	< 600 g/l
A.I.M. Category:	Waterproofing Sealer and Treatment Maximum VOC 600 g/l

Applicable Standards

- ASTM C-140 Moisture Absorption Barrier
- ASTM C-507 Wear Surface Strength
- ASTM C-672 Scaling
- D.O.T. Special Test Evaluating Surface Coating for concrete, salt and freeze/thaw deterioration

DRYING TIME:

At 72°F, TK-EPOXY WATERPROOFING COATING will cure in 4-6 hours and the surface may be reopened to traffic as soon as the coating is tack free. Within 72 hours the material will have completed it's intended results.

CLEAN UP:

Clean tools, equipment and spills with TK-00 SOLVENT* before the material dries.

COVERAGE:

The recommended rate of coverage for hardened (28 days old) concrete is two coats at 400 square feet per gallon. Existing, dusting concrete will require at least two coats at 400 square feet per gallon, and glossy finishes will require an additional coat.

As with any other type of concrete sealing compound, the porosity of the concrete and the type of finish will affect the actual coverage rate.

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

MAINTENANCE:

Minimal maintenance is required other than occasional sweeping, dusting or mopping.

LIMITATIONS:

- Apply in temperatures above 50°F.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-EPOXY WATERPROOFING COATING is available through TK Distributors. Contact TK Products for the nearest distributor.

Packaged in 10-gallon kit (5-gallon part A + 5-gallon part B) and 2 gallon kit (1-gallon part A + 1-gallon part B) units.

Available in two formulations:

1) TK-2671 (Low Solids) formulation meets the VOC content regulations of the Federal EPA. Maximum VOC content 600 g/l.

2) TK-2675 (High Solids) formulation meets the VOC content regulations of the Federal EPA, Ozone Transport Commission (OTC), and

Lake Michigan Air Directors Consortium (LADCO). Maximum VOC content 400 g/l.

FOR PROFESSIONAL USE ONLY

NOTES:

*TK-CHEMICAL CLEANER 101 must be purchased separately

*TK-00 SOLVENT must be purchased separately

03/16 Last Rev. 04/15

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.



TK Products Construction Coatings

11400 West 47th Street Minnetonka, MN 55343

800-441-2129 toll free | 952-938-8084 fax | www.tkproducts.com